

SPRAY ADHESIVE

AROMATIC-FREE, UNIVERSAL, LIQUID SPRAY ADHESIVE



PRODUCT DESCRIPTION

Aromatic-free, universal, liquid spray adhesive based on SBR rubber.

FIELD OF APPLICATION

For mutual bonding or temporary fixation of paper, cardboard, felt, fabric, cork, polystyrene foam, polyurethane foam and metal foils and to surfaces made of wood, hardboard, chipboard, glass, concrete and metal. Highly suitable for temporary fixation of templates.

PROPERTIES

- Bonds immediately
- Aromatics-free
- Universal
- Moisture resistant

PREPARATION

Working conditions: Do not use in temperatures $\leq +10^{\circ}\text{C}$.

Preliminary surface treatment: Clean and degrease the surfaces to be glued using Griffon Reiniger.

APPLICATION

Coverage: 5 m²/litre, applied on both sides.

Directions for use:

Shake Aerosol well before use.

Temporary fixation:

- 1) Apply adhesive thinly and evenly to one of the surfaces from a distance of approx. 25 cm.
- 2) Allow to dry for a minimum of 20 minutes.
- 3) Join materials and press firmly.

Permanent bonding:

- 1) Apply adhesive thinly and evenly to both surfaces from a distance of approx. 25 cm.
- 2) Allow to dry for a minimum of 10 minutes.
- 3) Join materials and knock, roll or press together firmly.

After spraying, hold the aerosol upside down and press the spray button until only propellant and no adhesive is emitted anymore. This prevents clogging of the aerosol.

Stains/residue: Wet adhesive residue can be removed using Griffon Cleaner. Dried adhesive residue can be removed mechanically or by using a paint stripper.

Points of attention: The technical data provided apply to the base adhesive without propellant.

CURE TIMES

Dry/Cure time: approx. 20 minutes (fixation); 10 minutes (permanent bonding).

* Curing time may vary depending on a.o. surface, product quantity used, humidity level and ambient temperature.

TECHNICAL PROPERTIES

Temperature resistance: From -40°C to $+50^{\circ}\text{C}$.

TECHNICAL SPECIFICATIONS

Chemical base: SBR Rubber

Viscosity: approx. 20 mPa.s.

Solid contents: approx. 22 %

Density: approx. 0.72 g/cm³

STORAGE CONDITIONS

A minimum of 24 months. Limited shelf life after opening. Store in a dry, cool and frost free place.

